

**DryWay Water Repellent Concrete Sealer****APPLICATION INSTRUCTIONS****PREPARATION**

The substrate must be structurally sound, thoroughly clean and dry. Remove all paints, sealers, or adhesives. Clean off oil, grease, dirt, wax, curing compounds, efflorescence, and other contaminants that might interfere with sealer penetration.

If acid is used for cleaning, neutralize completely the surface and rinse with water before application.

New concrete must be cured at least 28 days. If needed, caulk, patch, or repair the area prior to application.

Protect people, vehicles, property, plants, windows, and all non-masonry surfaces from the sealer, splash, residue, and wind drift. Divert foot and auto traffic.

**CONDITIONS**

Moisture inhibits penetration of the sealer, reducing the service life and performance of the treatment. After a rain, let dry for at least 24 hours. Do not apply outdoors when rain is expected within 12 hours.

Air and surface temperatures should be between 45 and 90 °F during application and for at least 8 hours after. Do not apply to hot surfaces in direct sunlight, or in strong wind.

**TOOLS**

Low-pressure sprayer (hand-pump garden sprayer or adjustable airless) with a fan tip nozzle, or a paint roller.

**APPLICATION**

Thoroughly shake the pail prior to opening and shake the filled hand-pump sprayer before application.

More porous surfaces may need two or more applications. Spray on additional applications "wet on wet" 5 to 10 minutes apart.

**VERTICAL APPLICATION**

Spray on from the bottom up creating a 4–6" controlled rundown below the spray contact point.

Do not over-apply. Spread out any runs or drips that do not penetrate with a roller.

**HORIZONTAL APPLICATION**

Apply a saturating film on the verge of puddling. Roll or broom out any puddles until the sealer penetrates into the substrate.

**DRYING & CURING**

The surface will dry to touch in one to two hours. Avoid foot or vehicle traffic until dry.

Water-repellent properties develop after 72 hours. Sealed surfaces will shed water or bead.

**RE-APPLICATION**

The surface will continue to shed water and protect the substrate for years, whether or not it beads.

The sealer adheres well to itself. It can be re-applied to increase beading or to restore water-shedding.

***DryWay Water Repellent Concrete Sealer***

---

**CLEANUP**

Using detergent and water, wipe off drips and overspray residue while still wet. Clean application equipment immediately after use. Removing dried sealer may require mechanical abrasion.

**STORAGE**

Store in a cool, dry place out of direct sunlight at temperatures below 90 °F. Protect from freezing.