



RadonSeal®

DEEP-PENETRATING CONCRETE SEALER

RadonSeal® Deep-Penetrating Concrete Sealer is a ready-to-use, reactive sealer, formulated for maximum penetration and sealing of capillaries in concrete and cementitious substrates. RadonSeal penetrates deep inside concrete (up to 4"), chemically reacts, bonds and strengthens concrete, restricting the movement of water, water vapor, soil gases, and even radon gas.



MOISTURE BLOCK



PERMANENT



STRENGTHENS



ZERO VOCs



NO-SLIP



PAINTABLE



BREATHABLE

ADVANTAGES

- **Waterproofing & Radon Mitigation** – Restricts the movement of water, water vapor, radon, and other soil gasses.
- **Strengthens** – Bonds and hardens concrete surfaces, reducing dusting, spalling, and cracking. Protects concrete against freeze/thaw damage, road salts and deicing chemicals.
- **Efflorescence** – Reduces efflorescence (unsightly mineral salts).
- **ECO-Friendly** – Zero VOCs, no solvents, no noxious odors. Safe for indoor use.
- **Breathable** – Does not trap water vapor at the surface. Allows concrete to breath and dry.
- **Non-Film Forming** – Does not change appearance or make surfaces slippery.
- **Paintable** – Neutralizes alkalis and reduces high pH (new concrete). Improves the performance of water-based stains, epoxy coatings, paints, thinset, patching compounds and surface levelers.
- **Deep-Cleans** – Purges contaminants, sub-efflorescence, minor oil and grease spills, and animal urine to the surface.
- **Permanent** – One time application. No reapplication required. Cannot be pushed out by water pressure, will not wear off.

USES

RadonSeal works by reacting with Portland Cement, it is most effective when used on high-quality concrete (+3" thick, indoor/outdoor);

- **Poured Concrete** - Basement walls and floors. Garage slabs. Slab-on-grade construction. Factory and warehouse floors. Driveways, sidewalks, pool decks, patios, car ports, concrete curbs, parking lots, seawalls, storage tanks, cooling towers, concrete columns, building facades.
- **Concrete Blocks** - Heavyweight concrete blocks, cinder blocks, foundation walls, retaining walls.
- **Limestone** - Basements walls constructed from limestone and concrete. Limestone building facades and columns
- **Mortar** - Solidifies mortar between concrete blocks and porous mortar in older stone foundation walls.

LIMITATIONS

- RadonSeal Concrete Sealer is an impregnating sealer. Not a topical sealant or coating system. It does not seal water penetration due to structural defects, cracks, seams, corner joints, holes, and similar which may require caulking, patching, or other crack repair materials.
- Not intended for use on fiber-reinforced concrete, stamped concrete, color-stained concrete, lightweight blocks, dry-pressed, spilt face, haydite, popcorn blocks, brick, pavers, flagstone, and grout.

APPLICATOR

RECOMMENDED – Apply using a hand-pump sprayer equipped with fan tip nozzle.

If spray application is not practical, a heavy-nap paint roller or brush can be used.

COVERAGE

- **Poured Concrete:** 200 sq. ft. per gallon.
- **Concrete Blocks:** 100 sq. ft. per gallon.
- **Cinder Blocks:** 80 sq. ft. per gallon.
- **Stucco:** 200-250 sq. ft. per gallon.
- **Limestone:** 175-225 sq. ft. per gallon.

(Coverage is estimated)



TECHNICAL DATA

Physical Form:	Liquid	Boiling Point:	214°F
Odor:	No/Low Odor	Freeze Point:	32°F
Color:	Colorless, Turbid	VOC Content:	Zero
Specific Gravity:	(H2O=1) 1.2@ 24° C.	Shelf Life:	1 Year
pH:	11.5 liquid / 7.9 cured	Storage:	40-90 °F
Solubility in Water:	Excellent	Evaporation Rate:	Same as water

PERFORMANCE DATA

Water Absorption Reduction I Poured Concrete	ASTM C-642	98%
Absorbed Chloride Reduction	NCHRP 244	< 6%
Efflorescence	ASTM-C-67 Section 29	High resistance to efflorescence
Increase in compressive strength	ASTM C 39	45%
Increase in surface hardness. Increase in wear resistance.	ASTM C 779	45% > 200%
Increase in epoxy adhesion	ASTM D 3359	20%
Moisture retention / Concrete curing	ASTM-C-156	Significant improvement in curing against hairline cracking and spot drying.
Resistance to Sunlight (UV)	Excellent I UV Stable	
Bacterial Growth	Does Not Support	
Resistance to Alkalinity	Excellent	
Surface Appearance	No Color Change No Gloss	
Paint adhesion	Treated surfaces are compatible with any type of covering.	
Drying Time	1-4 Hours	

United States Department of Agriculture - USDA Compliant
US Environmental Protection Agency - EPA Compliant



PACKAGING



CHEMICAL RESISTANCE

The resistance rating is based on a combination of the concrete resistance to penetration, absorption, disintegration, and the ability to recover and stabilize. Acids were tested in a 10% solution and all other liquids at full strength as normally sold and used.

Excellent	Sodium Chloride (Salt) NaCl	Grain Alcohol C2H5OH
	Motor Oil	Hydraulic Fluid
	Kerosene	Mineral Spirits
	Grain Alcohol C2H5OH	Wood Alcohol CH3OH
	Vegetable Oil	Mineral Oil
	Turpentine	
Good	Gasoline	Xylene
	Toluene	Acetone CH3OOOH3
	Hydrochloric Acid HCL	Sulfuric Acid H2SO4
	Nitric Acid HNO3	Phosphoric Acid H3PO4
	Sodium Hydroxide NaOH	Potassium Hydroxide KOH
	Ammonia NH3	Hydrogen Sulfide H2S

PRODUCT DISCLAIMER

The information and recommendations made are based on our own research and the research of others, and are believed to be accurate. Because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that the Product is safe, effective, and suitable for its intended end use. Novion, Inc. specifically disclaims liability for any incidental, consequential or other damages including but not limited to, loss of profits or damages to a structure or its contents. Read and understand the product Safety Data Sheets (SDS) prior to use.